



Standard Specification for Crosslinked and Noncrosslinked Poly(Vinyl Chloride) Heat- Shrinkable Tubing for Electrical Insulation¹

This standard is issued under the fixed designation D 3150; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification applies to flexible, crosslinked and noncrosslinked poly(vinyl chloride) heat-shrinkable tubing for electrical insulating purposes. It is supplied in an expanded form and will shrink to its extruded diameter when heated.

NOTE 1—This standard is similar but not identical to IEC 60684–3–201.

1.2 The values stated in inch-pound units are to be regarded as the standard except temperature, which shall be stated in degrees Celsius. Values in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

- D 1711 Terminology Relating to Electrical Insulation²
- D 2671 Test Methods for Heat-Shrinkable Tubing for Electrical Use²
- D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials²
- E 176 Terminology of Fire Standards³

2.2 Military Standards:⁴

- MIL-STD-104 Limits for Electrical Insulation Color
- MIL-H-5606 Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance
- MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4 and JP-5
- MIL-L-7808 Lubricating Oil, Aircraft, Turbine Engine, Synthetic Base
- MIL-L-23699 Lubricating Oil, Aircraft, Turbine Engines, Synthetic Base
- MIL-A-8243 Anti-Icing and De-Icing Defrosting Fluid

2.3 Federal Standards:

- SS-S-550 Sodium Chloride, Technical, for Water-Softening Units⁵

2.4 IEC Standards:

- 60684–3–201 Flexible insulating sleeving, Part 3, Sheet 201: Heat shrinkable sleeving, general purpose, flexible, cross-linked PVC, shrink ratio 2:1⁶

3. Terminology

3.1 Definitions:

3.1.1 For definitions pertaining to electrical insulation, refer to Terminology D 1711.

3.1.2 For definitions pertaining to fire standards, refer to Terminology E 176.

4. Classification

4.1 *Type I*—Flexible, noncrosslinked poly(vinyl chloride) tubing capable of being shrunk at 135°C (275°F) in 15 min.

4.2 *Type II*—Flexible, crosslinked poly(vinyl chloride) tubing capable of being shrunk at 175°C (347°F) in 15 min.

5. Ordering Information

5.1 When tubing is ordered to this specification, the purchaser should define the size, color, and type of the required tubing.

6. Materials and Manufacture

6.1 The polymers used in the manufacture of heat-shrinkable tubing shall be modified poly(vinyl chloride) and the finished compound shall be free of all foreign matter other than intended formulation additives as appropriate.

6.2 The tubing shall be extruded, crosslinked (Type II only), and then expanded to the required dimensions.

7. Chemical and Physical Property Requirements

7.1 The material shall conform to the chemical and physical property requirements specified in Table 1.

7.2 Every lot of material shall be tested for dimensional requirements, restricted shrinkage, tensile strength, elongation, longitudinal change, and dielectric breakdown. Other requirements may be tested less frequently or at a frequency agreed upon between the supplier and the purchaser.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved Apr. 10, 2000. Published July 2000. Originally published as D 3150 – 73. Last previous edition D 3150 – 95.

² *Annual Book of ASTM Standards*, Vol 10.02.

³ *Annual Book of ASTM Standards*, Vol 04.07.

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁵ May be obtained from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

⁶ Available from American National Standards Institute, 11 W. 42nd St., New York, NY 10036.

TABLE 1 Chemical and Physical Property Requirements

Property	Requirements	
	Type I	Type II
Restricted shrinkage, Procedure A: Type I—30 min, 135 ± 2°C (275 ± 4°F) Type II—30 min, 175 ± 2°C (374 ± 4°F) 2000-V proof voltage	no cracks	no cracks no failures
Longitudinal change, max, %	0, - 25	+ 1, - 10
Dielectric strength, V/mil (kV/mm)	400 (15.75)	400 (15.75)
Color	MIL-STD-104	MIL-STD-104
Color stability, 24 h at 130 ± 2°C (266 ± 4°F)	MIL-STD-104	MIL-STD-104
Water absorption, 24 h at 25 ± 2°C (77 ± 4°F), max, %	1.0	1.0
Specific gravity, max	1.40	1.40
Volume resistivity, min, ohm-cm	10 ¹¹	10 ¹¹
Flammability, max, s, Procedure A	15	15
Heat shock: Type I—4 h at 180 ± 2°C (236 ± 4°F) Type II—4 h at 200 ± 2°C (392 ± 4°F)	no dripping, flowing, or cracking	no dripping, flowing, or cracking
Low-temperature flexibility, Procedure B, all sizes 1 h at - 10°C (14°F) on as-received specimens	no cracking	no cracking
Tensile strength, min, psi (MPa)	2000 (13.8)	2000 (13.8)
Elongation, min, %	200	200
Heat resistance, 168 h at 136 ± 2°C (277 ± 4°F), followed by tests for:		
Elongation, min, %	150	130
Elongation, % of original, min	65	65
Fluid resistance, 24 h at 25 ± 2°C (77 ± 4°F): Hydraulic Fluid, MIL-H-5606 JP-4 Fuel, MIL-T-5624 Lubricating Oil, MIL-L-7808 Lubricating Oil, MIL-L-23699 De-icing Fluid, MIL-A-8243 5 % NaCl, SS-S-550 Followed by tests for:		
Dielectric strength, V/mil (kV/mm)	280 (11.0)	280 (11.0)
Tensile strength, min, psi (MPa)	1800 (12.4)	2000 (13.8)
Copper corrosion, Procedure B: 168 h at 136°C (277°F)	no blackening or pitting of copper	no blackening or pitting of copper
Copper dust humidity test, Procedure C	no corrosion or discoloration of copper dust	no corrosion or discoloration of copper dust
Shelf life		
The required shelf life is 2 weeks at 40 ± 2°C (104 ± 4°F). The supplier must advise and caution the customer if special storage and handling precautions must be observed to maintain required product dimensions and characteristics.		

8. Dimensional Requirements

8.1 Type I material shall conform to the applicable requirements listed in Table 2 or Table 3.

8.2 Type II material shall conform to the requirements listed in Table 3.

TABLE 2 Type I Dimensions

As Supplied		After Unrestricted Shrinkage	
Nominal Size, in.	Inside Diameter, min, in. (mm)	Inside Diameter, max, in. (mm)	Wall Thickness, in. (mm)
1/16	0.063 (1.60)	0.037 (0.94)	0.014 ± 0.003 (0.35 ± 0.08)
3/32	0.093 (2.34)	0.055 (1.41)	0.014 ± 0.003 (0.35 ± 0.08)
1/8	0.125 (3.18)	0.075 (1.91)	0.014 ± 0.003 (0.35 ± 0.08)
3/16	0.187 (4.75)	0.110 (2.80)	0.018 ± 0.003 (0.45 ± 0.08)
1/4	0.250 (6.35)	0.150 (3.81)	0.022 ± 0.004 (0.56 ± 0.12)
3/8	0.375 (9.5)	0.225 (5.71)	0.022 ± 0.004 (0.56 ± 0.12)
1/2	0.500 (12.7)	0.300 (7.61)	0.022 ± 0.004 (0.56 ± 0.12)
3/4	0.750 (19.7)	0.450 (11.4)	0.022 ± 0.004 (0.56 ± 0.12)
1	1.000 (25.4)	0.600 (15.25)	0.022 ± 0.004 (0.56 ± 0.12)
1 1/2	1.500 (38.1)	0.900 (22.9)	0.034 ± 0.005 (0.86 ± 0.13)
2	2.000 (50.1)	1.200 (30.5)	0.034 ± 0.005 (0.86 ± 0.13)
3	3.000 (76.4)	1.800 (45.8)	0.034 ± 0.005 (0.86 ± 0.13)
4	4.000 (101.6)	2.400 (61.0)	0.034 ± 0.005 (0.86 ± 0.13)
5	5.000 (127.0)	3.000 (76.3)	0.034 ± 0.005 (0.86 ± 0.13)
6	6.000 (152.5)	3.600 (91.5)	0.034 ± 0.005 (0.86 ± 0.13)

TABLE 3 Type I and II Dimensions

Nominal Size, in.	As Supplied		After Unrestricted Shrinkage
	Inside Diameter, min, in. (mm)	Inside Diameter, max, in. (mm)	Wall Thickness, in. (mm)
3/64	0.046 (1.16)	0.023 (0.59)	0.020 ± 0.003 (0.51 ± 0.08)
1/16	0.063 (1.60)	0.031 (0.76)	0.020 ± 0.003 (0.51 ± 0.08)
3/32	0.093 (2.34)	0.046 (1.16)	0.020 ± 0.003 (0.51 ± 0.08)
1/8	0.125 (3.18)	0.062 (1.60)	0.025 ± 0.003 (0.63 ± 0.08)
3/16	0.187 (4.75)	0.093 (2.34)	0.025 ± 0.003 (0.63 ± 0.08)
1/4	0.250 (6.35)	0.125 (3.18)	0.025 ± 0.003 (0.63 ± 0.08)
3/8	0.375 (9.50)	0.187 (4.75)	0.030 ± 0.005 (0.76 ± 0.13)
1/2	0.500 (12.7)	0.250 (6.35)	0.030 ± 0.005 (0.76 ± 0.13)
3/4	0.750 (19.1)	0.375 (9.50)	0.035 ± 0.005 (0.89 ± 0.13)
1	1.000 (25.4)	0.500 (12.7)	0.040 ± 0.005 (1.02 ± 0.13)
1 1/2	1.500 (38.1)	0.750 (19.1)	0.045 ± 0.006 (1.15 ± 0.15)
2	2.000 (50.1)	1.000 (25.4)	0.050 ± 0.007 (1.27 ± 0.18)

8.3 Tubing with non-standard dimensions may be supplied when agreed upon between purchaser and seller. Tubing with non-standard dimensions shall be considered to comply with this specification if the requirements of Table 1 and Table 2 are satisfied and the minimum recovered wall thickness equals or exceeds that of the identical or next largest as supplied size. The wall for sizes greater than the largest specified size shall be at least as thick as that of the largest specified size.

9. Workmanship

9.1 The tubing shall be homogeneous and free of flaws, defects, pinholes, bubbles, seams, cracks, or inclusions that may detrimentally affect its suitability for the service intended.

10. Sampling

10.1 A lot shall consist of all material that is processed at the same time and under the same conditions and submitted for inspection at one time.

10.2 Properties may be tested at any stage in processing when they are unaffected by subsequent processing.

10.3 Select a quantity of the product at random from each lot in accordance with Practice D 3636 and Table 4.

10.4 Statistical process control measurements may be used to demonstrate conformance in lieu of the sampling plan noted herein when the demonstrated process capability is greater than the specified AQL.

11. Number of Tests and Retests

11.1 The methods of test define the number of specimens and length required for each test.

11.2 If the results of any test, except for attributes listed in Table 2 and Table 3, do not conform to the requirements prescribed in this specification, perform two additional tests on different specimens from the same lot. Nonconformance to Table 2 and Table 3 requirements on first inspection shall be cause for rejection.

11.3 If either of the two additional tests results in a nonconformance, the lot of material may be rejected at the option of the purchaser. Notice of nonconformance based on tests made according to this specification shall be reported to the manufacturer within 60 days from receipt of the material by the purchaser.

TABLE 4 Sampling Table for Lot Acceptance Tests

Property	Requirement	Inspection Level	AQL	Sampling Unit, ft (m)
Inside diameter as supplied	Table 2 or Table 3	S-3	1.0	4 (1.2)
Inside diameter after unrestricted recovery	Table 2 or Table 3	S-3	1.0	4 (1.2)
Wall thickness after shrinkage	Table 2 or Table 3	S-3	1.0	4 (1.2)
Longitudinal change	Table 1	S-2	1.0	4 (1.2)
Workmanship	8.1 herein	I	2.5	4 (1.2)

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

11.4 Tubing that has been rejected may be replaced or reworked to correct the defects and resubmitted for inspection. Before resubmitting, full particulars concerning previous rejection and action taken to correct the nonconformances shall be furnished to the inspector.

12. Test Methods

12.1 The test methods described in Test Methods D 2671 shall be used unless otherwise stated in Table 1.

12.2 To recover (shrink) heat-shrinkable tubing described in this specification, the following shall be used:

Type I—15 min at $135 \pm 5^\circ\text{C}$ ($275 \pm 9^\circ\text{F}$)

Type II—15 min at $175 \pm 6^\circ\text{C}$ ($347 \pm 10^\circ\text{F}$)

13. Inspection

13.1 The manufacturer or the purchaser or both shall have available all the facilities to enable the complete testing to this specification.

14. Certification

14.1 When specified in the purchase order or contract, the manufacturer's or supplier's certification shall be furnished to the purchaser stating that samples representing each lot have been manufactured, tested, and inspected in accordance with this specification and the requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

15. Packaging, Marking, and Shipping

15.1 The tubing shall be supplied in continuous rolls, or in lengths as mutually agreed upon between the manufacturer and the purchaser.

15.2 The tubing shall be packaged in conformance with good commercial practice unless otherwise specified. Individual sizes, types, lengths, and colors shall be bundled and spooled and properly identified, specifying size, type, quantity, color, and material.

15.3 The bundles or spools shall then be placed in corrugated boxes, and shall be taped in a manner that shall be accepted by parcel post or common carrier.

16. Keywords

16.1 crosslinked poly(vinyl chloride) heat-shrinkable tubing; electrical insulation; heat-shrinkable tubing; poly(vinyl chloride); poly(vinyl chloride) heat-shrinkable tubing