



Standard Test Methods of Sampling and Testing Pulp to be Used in the Manufacture of Electrical Insulation¹

This standard is issued under the fixed designation D 3376; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the sampling and testing of cellulosic pulps for use in the manufacture of electrical insulating papers and boards or in the direct application of pulp fibers as insulation to electrical conductors.

NOTE 1—The significance of any one pulp property test method, as set forth herein, should be considered with discretion depending on the product made from the pulp.

1.2 Sections on Reagents, Sampling, and Report are integral parts of each of the individual test methods that follow.

1.3 Each test method is described as being a measure of either a bulk property of the pulp or a property of a handsheet formed from the pulp.

1.3.1 Bulk characteristics determinable by these procedures appear in the following sections:

Procedure	Sections	ASTM Method Reference	TAPPI Method Reference
Aqueous Extract Conductivity	8 and 9	D 202	...
Aqueous Extract pH	10 and 11	D 202	...
Aqueous Extractable Acidity-Alkalinity	12 and 13	D 202	...
Analysis of Ash for Cations by Atomic Absorption Spectrophotometry	73-81	D 1193 and D 2576	...
Ash Content	82-85	D 202	T 413
Dirt in Pulp	42 and 43	...	T 213
Fiber Analysis	24 and 25	D 202 and D 1030	...
Fiber Length of Pulp	44 and 45	...	T 232, T 233
Freeness (Canadian Standard Freeness)	56 and 57	...	T 227
Kappa Number/Permanganate Number (Substances Oxidizable by Permanganate)	28 and 29	...	T 236, UM 251
Laboratory Processing of Pulp (Beater Method)	54 and 55	...	T 200
Moisture in Pulp	32-34	...	T 210

Neutral Aqueous Extractable Hardness in Pulp	16-23	D 202, D 1126, and D 2576	...
Pentosan Content of Pulp	30 and 31	...	T 223
Resistance of Pulp to Disintegration (Standard RPG)	46-53	...	T 239, UM 252
Shive Count	35-41
Solvent-Soluble Matter in Pulp	26 and 27	D 202	...
Tensile Properties	68-72	D 202	...
Water-Extractable Chlorides	14 and 15	D 202	...

1.3.2 Handsheet characteristics determinable by these procedures appear in the following sections:

Procedure	Section	ASTM Method Reference	TAPPI Method Reference
Air Resistance (Porosity)	60 and 61	D 202	T 205
Apparent Density	66 and 67	D 202	T 205
Bursting Strength	62 and 63	D 202 and D 774	T 205
Folding Endurance (M.I.T.)	54 and 55	D 202 and D 2176	T 205
Forming Handsheets for Physical Tests of Pulp	58 and 59	...	T 205
Tensile Strength	68 and 69	D 202 and D 828	T 205

NOTE 2—Methods for Ash, Silica, selected cations from Ash, Heat Stability, α, β, and γ Cellulose, Viscosity, Total Chlorine, Tear, and Dissipation Factor and Relative Permittivity, will be considered for addition as methods are developed.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

¹ These test methods are under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and are the direct responsibility of Subcommittee D09.19 on Dielectric Sheet and Roll Products.

Current edition approved Nov. 25, 1988. Published May 1989. Originally published as D3776 – 75. Last previous edition D3776 – 83.

- D 202 Test Methods for Sampling and Testing Untreated Paper Used for Electrical Insulation²
- D 774 Test Method for Bursting Strength of Paper³
- D 828 Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus³
- D 1030 Test Method for Fiber Analysis of Paper and Paperboard³
- D 1126 Test Method for Hardness in Water⁴
- D 1193 Specification for Reagent Water⁴
- D 2176 Test Method for Folding Endurance of Paper by the M.I.T. Tester³
- D 2576 Test Method for Metals in Water and Waste Water by Atomic Absorption Spectrophotometry⁵
- D 3376 Test Methods for Sampling and Testing Pulps to be Used in the Manufacture of Electrical Insulation⁶
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁷
- 2.2 *TAPPI Standards*:⁸
- T 200 Laboratory Processing of Pulp (Beater Method)
- T 205 Forming Handsheets for Physical Tests of Pulp
- T 210 Weighing, Sampling, and Testing Pulp for Moisture
- T 213 Dirt in Pulp
- T 220 Physical Testing of Pulp Handsheets
- T 221 Drainage Time of Pulp
- T 222 Insoluble Lignin in Wood and Pulp
- T 223 Pentosans in Wood and Pulp
- T 227 Freeness of Pulp
- T 232 Fiber Length of Pulp by Projection
- T 233 Fiber Length of Pulp by Classification
- T 236 Kappa Number of Pulp
- T 413 Ash in Paper and Paperboard
- T 445 Identification of Specks and Spots in Paper
- T 1002 Drainage Time for Insulating Board
- UM 203 Freeness of Pulp (William Tester)
- UM 251 Permanganate Number of Pulp
- UM 252 Resistance of Pulp and Paper Stock to Disintegration

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *pulp, n*—a fibrous material that is made by chemical or mechanical treatment, or both, of wood, cotton, hemp, or other cellulosic fiber to achieve substantially separate fibers that are suitable for a sheet-forming process.

NOTE 3—Electrical insulation made from pulp may be papers or boards used for capacitors, transformer coils, creped papers, etc. It may also be pulp applied directly onto electrical conductors.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Annual Book of ASTM Standards*, Vol 15.09.

⁴ *Annual Book of ASTM Standards*, Vol 11.01.

⁵ Discontinued; see 1980 *Annual Book of ASTM Standards*, Part 31.

⁶ *Annual Book of ASTM Standards*, Vol 10.02.

⁷ *Annual Book of ASTM Standards*, Vol 14.02.

⁸ TAPPI Standards and Provisional Methods are available from Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30338.

4. Summary of Test Methods

4.1 These test methods describe the specific procedures for testing the properties of pulp, both in its original bulk form and after it has been formed into a handsheet in the testing laboratory.

5. Reagents

5.1 *Purity of Reagents*—Use reagent grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁹ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean water conforming to Specification D 1193, Type III.

6. Sampling

6.1 Terminology regarding sampling and evaluation terminology shall conform to those in the sampling sections of Test Methods D 202.

6.2 Obtain the sample of pulp from the lot to be evaluated in a manner that will maximize the probability that a representative sample is collected. Where practicable, use one of the sampling plans shown in Test Methods D 202. Protect the material sample from contamination during handling and transporting to a laboratory for testing. The instructions for preparation of specimens are given in the sections pertaining to the individual property tests. Take the sample for moisture content in accordance with TAPPI T 210.

6.3 Condition samples in a container suitable for preventing moisture variation over the period of testing. When test specimens are drawn, determine the moisture content of the material to allow correction of weights to moisture-free equivalent weight.

7. Report

7.1 At the completion of any or all of the following tests, report the test results (as defined in 6.1) of the pulp properties with identifying units as follows:

7.1.1 Identification of the pulp sampled and tested by lot number, type, grade, etc.,

7.1.2 Dates of testing,

7.1.3 Location of the testing laboratory and the person responsible for the testing,

7.1.4 Remarks indicating method or procedures used and the deviation, if any, from the standard test procedures,

7.1.5 Indication of the variance in test measurements (as defined in 6.1) such as high, low, standard deviation, etc., and

7.1.6 Any information particular to the cited procedure.

⁹ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

7.2 Report the test results (as defined in 6.1) as calculated or observed values rounded to the nearest unit in the last right-hand place of figures used in the material specification to express the limiting value. (See the rounding method of Practice E 29.)

AQUEOUS EXTRACT CONDUCTIVITY

8. Significance and Use

8.1 The conductivity of the water extract of electrical grade pulp results from electrolytic impurities in the pulp which may be present as ionizable acids, bases, salts, or a combination of these. The presence of electrolytic impurities in electrical insulation is undesirable as they tend to lower insulation resistance and have corrosion-producing tendencies under conditions of applied potential. When comparing test data it should be noted that the extract conductivity of pulps, especially those of high purity, may change with time after manufacturing. This test is useful for routine acceptance testing, the comparison of different pulps, and research work.¹⁰

9. Procedure

9.1 Follow Test Methods D 202 except use a specimen weight equivalent to 1 g of moisture-free pulp.

AQUEOUS EXTRACT pH

10. Significance and Use

10.1 The extract pH determination measures the degree to which a pulp alters the hydrogen-hydroxyl equilibrium of pure water. The test gives a measure of the active acidity or alkalinity of the pulp extract. The presence of active acidic or alkaline contaminants in a pulp may result in their being incorporated into the electrical insulation made from the pulp, and can lead to a deterioration of the insulation in service. This test is useful for routine acceptance testing, the comparison of different pulps, and research work.⁷

11. Procedure

11.1 Follow Test Methods D 202 except use a specimen weight equivalent to 1 g of moisture-free pulp.

AQUEOUS EXTRACTABLE ACIDITY-ALKALINITY

12. Significance and Use

12.1 The extract acidity-alkalinity determination for a pulp measures the quantity of extracted ionizable material, which alters the hydrogen-hydroxyl equilibrium of pure water. The presence of active acidic or alkaline contaminants in a pulp may result in their being incorporated into the electrical insulation made from the pulp, and can lead to a deterioration of the insulation in service. This test is useful for routine acceptance testing, the comparison of different pulps, and research.⁸

13. Procedure

13.1 Follow Test Methods D 202 except use a specimen weight equivalent to 1 g of moisture-free pulp.

WATER-EXTRACTABLE CHLORIDES

14. Significance and Use

14.1 The occurrence of significant amounts of chloride ion in a pulp may lead to the incorporation of the ion in the electrical insulation made from the pulp. The presence of chloride ions may adversely affect the electrical properties and service life of the insulation. This test is useful for routine acceptance testing, the comparison of different pulps, and research testing.

15. Procedure

15.1 Follow Test Methods D 202 except use a specimen weight equivalent to 4 g of moisture-free pulp. For pulps with higher levels of chloride (greater than 30 ppm) 10 min of masceration as in the above method for aqueous extract conductivity may be used to hasten the extraction followed by 1 h refluxing as in Test Methods D 202. When the chloride content is less than 30 ppm, masceration is not permitted. The appropriate extraction time must be determined to give complete extraction of the chloride for each pulp type. Times greater than 1 h may be necessary.

NEUTRAL AQUEOUS EXTRACTABLE HARDNESS PULP

16. Terminology

16.1 *Definitions of Terms Specific to This Standard:*

16.1.1 *aqueous extractable hardness, n*—the amount of calcium and magnesium present in pulp and which may be extracted by hot neutral water under prescribed conditions.

16.1.2 *hardness, n*—a characteristic of water that represents the total concentration of calcium and magnesium in the water expressed as parts per million (ppm) CaCO₃.

17. Significance and Use

17.1 Cellulose pulps may contain varying amounts of aqueous extractable hardness as supplied to the purchaser. The dissolved hardness from the pulp may accumulate in process water used in wet-forming methods and may interfere with the action of process additives and affect product quality adversely.

17.2 Method A is the preferred method and shall be used for reference purposes.

METHOD A

18. Procedure

18.1 *Extraction:*

18.1.1 Prepare extracts of the pulp specimens in accordance with the Test Methods D 202 method for aqueous extract conductivity, except:

18.1.2 Use a specimen weight equivalent to 2.0 g of moisture-free pulp. Determine the moisture content of the pulp sample on a separate specimen taken at the same time as the test specimen.

¹⁰ For more detailed information see *Paper and Paperboard—Characteristics, Nomenclature, and Significance of Tests*, ASTM STP 60 B, Am. Soc. Testing Mats., 1963, pp. 59–61.

18.1.3 The extraction volume shall be 200 mL.

18.1.4 Run a blank determination concurrently with the test specimen determination.

18.1.5 Following extraction and filtration, collect the clear filtrate and adjust the volume to exactly 200 mL.

18.2 Determine the calcium and magnesium concentration of the extract in accordance with Test Method D 2576.

19. Calculation

19.1 Calculate the hardness of the extracts as follows:

$$\text{Hardness, ppm} = 100[2.497(P_1 - P_a) + 4.117(P_2 - P_b)] \quad (1)$$

where:

P_1 = ppm calcium in the pulp extract,

P_a = ppm calcium in the blank,

P_2 = ppm magnesium in the pulp extract, and

P_b = ppm magnesium in the blank.

METHOD B

20. Procedure

20.1 Follow the procedure of Method A for the preparation of the extract.

20.2 Take two 100-mL aliquots of the extract and titrate for total hardness following the “low total hardness” procedure of the nonreferee volumetric method of Test Method D 1126.

21. Calculation

21.1 Calculate the hardness of the specimen extract as follows:

$$\text{Hardness, ppm} = 500 (V_1 + V_2 - V_a - V_b) \quad (2)$$

where:

V_1 = standard EDTA solution for titration of first aliquot of extract, mL

V_2 = standard EDTA solution for titration of second aliquot of extract, mL

V_a = standard EDTA solution for titration of first blank aliquot, mL, and

V_b = standard EDTA solution for titration of second blank aliquot, mL.

22. Report

22.1 Report the results as neutral aqueous extractable hardness, ppm, expressed as calcium carbonate according to the appropriate method of Test Methods D 3376.

23. Precision and Bias

23.1 The precision of this test has not been determined. No statement can be made about the bias of this test since standard material is not available.

FIBER ANALYSIS

24. Significance and Use

24.1 The fiber composition of a pulp (fiber source and pulping treatment) strongly affects the ultimate product characteristics. Fiber analysis is useful both as a specification and as a control test, and may be used in referee testing or research.

NOTE 4—For accurate results the analyst should have considerable training and experience. The analyst should make frequent use of standard fiber sources of known composition, or of authentic fiber samples, and be thoroughly familiar with different fibers and their behavior when treated with the various stains.

25. Procedure

25.1 Follow Test Methods D 202 and D 1030 using a specimen weight of 0.2 g of pulp drawn from a composite sample of pulp equivalent to 30 g of moisture-free pulp disintegrated in 2 L of water as in Test Method D 1030 and the section on Fiber Analysis of Test Methods D 202.

SOLVENT-SOLUBLE MATTER IN PULP

26. Significance and Use

26.1 Since pulping processes usually remove most water-soluble and volatile compounds that are also soluble in organic solvents, the solvent extractives in pulp may be considered to consist primarily of resin and fatty acids, their esters, waxes, and unsaponifiable substances. No single organic solvent is capable of removing all these substances, and different solvents remove different combinations. The mixture of 1 part by (volume) of 95 % ethanol and 2 parts of benzene appears to provide the most complete removal of all solvent-extractable substances in pulp.

26.2 Solvent-extractable materials, if present in sufficient quantity in electrical insulation, may lower the quality of the insulation or have a deleterious effect on the liquid compounds used in contact with insulation in various types of apparatus. Ethanol-soluble materials in capacitor paper have been found to increase the conductivity of chlorinated organic compounds, which are used as impregnants in capacitors. A combination of ether and alcohol-benzene extractives is reported to represent the quantity of pitch in wood pulp. Pitch in pulp may cause operating problems in the paper mill, such as the plugging of felts, wires, etc.

26.3 This method, with solvent or solvents specified, may be used for routine acceptance testing, comparing different pulps, and research tests.

27. Procedure

27.1 Test for solvent-soluble matter in accordance with Test Methods D 202.

KAPPA NUMBER/PERMANGANATE NUMBER (SUBSTANCES OXIDIZABLE BY PERMANGANATE)

28. Significance and Use

28.1 The permanganate consumption of a pulp is a measure of its lignin content and may be used as a measure of lot-to-lot uniformity. For a given species of wood or other fibers, the permanganate consumption is a measure of the degree of cooking to which the fiber has been subjected, and can relate to the ease of refining of the pulp produced from the cooked fiber. This test is useful for control purposes, specifications, and the comparison of different pulps.

29. Procedure

29.1 *Kappa Number*—Follow TAPPI T 236.

29.2 *Permanganate Number*—Follow TAPPI UM 251.

PENTOSAN CONTENT OF PULP

30. Significance and Use

30.1 The pentosan content of a pulp strongly affects the dissipation factor—temperature relationship of electrical insulation made from it. It also may be an indicator of lot-to-lot uniformity and is one of several factors related to the bonding power of a pulp, and the amount of energy required to refine the pulp.

31. Procedure

31.1 Follow TAPPI T 223.

MOISTURE IN PULP

32. Significance and Use

32.1 Pulp is purchased on the basis of moisture content. In addition, the moisture content may be used for consistency control, and it may affect the energy of repulping and the biological degradation of the pulp. This test is useful for control purposes and specifications.

33. Procedure

33.1 Follow TAPPI T 210.

34. Report

34.1 This method gives the percentage moisture content of the pulp. Report percent water and percent moisture-free fiber (equal to 100 minus percent water).

SHIVE COUNT

35. Terminology

35.1 *Definitions of Terms Specific to This Standard:*

35.1.1 *shive, n*—a particle in pulp or paper that is a bundle of cellulosic fibers bonded together in a parallel arrangement.

NOTE 5—Dark single fibers are not to be counted as shives. Count only bundles of fibers regardless of color.

35.1.2 *shive count, n*—the quantitative expression of the concentration of shives in a quantity of pulp or paper. For this method the shive count is restricted to the number of shives that exceed 1.5 mm in length that are present after a specified processing of the pulp to form handsheets for evaluation.

36. Significance and Use

36.1 Several grades of electrical insulating paper are most effectively manufactured using pulps having a low shive count. Shives in wood pulp to be used for direct application to electrical conductors can be detrimental to the insulating characteristics and strength of the insulating wall. This test is useful for control purposes, specifications, and the comparison of different pulps.

37. Apparatus

37.1 *Disintegrator, Sheet Machine, Press, Blotters, etc.*, in accordance with TAPPI T 205.

37.2 *Steel Rule*, graduated in 0.5 mm.

37.3 *Balance*, to weigh up to 100 g with 0.1-g accuracy.

37.4 *Specimen Viewer* with white opaque glass and a fluorescent or incandescent light source.

37.5 *Transparent Cylinder*, 0.6 L.

38. Procedure

38.1 From the sample obtained as specified in Section 6, take a quantity of pulp equivalent to 30 g of moisture-free pulp. Soak this pulp in 0.5 L of water for 4 h at a temperature of 20 to 30°C.

38.2 Tear the pulp into smaller pieces (approximately 1 in. or 25 mm square) and dilute to 2.0 L. **Caution**—*Tear*, do not cut the pulp.

38.3 Using the TAPPI disintegrator, disintegrate for 10 minute minimum. This time should be sufficient to disperse the pulp completely. A technique for checking the dispersion is as follows:

38.3.1 Take a small sample of the slurry from the disintegrator (about 2 or 3 mL) and dilute to 0.6 L in a clear cylinder. Stopper the cylinder and mix the suspension by rotating the cylinder end over end. Observe the suspension by looking through it toward a strong light source. The suspension should be free of clumps or agglomerates of fibers, but may contain shives. If the suspension contains clumps or agglomerates, subject the pulp to additional 5-min periods of disintegration until it is free of clumps and agglomerates.

38.4 Dilute the disintegrated pulp with water to result in a consistency of 0.3 % or 3 g/L.

38.5 Clean the sheet machine thoroughly.

38.6 Form handsheets in accordance with TAPPI T 205 and couch but do not dry the sheets.

38.7 Make at least five handsheets for viewing.

38.8 On each of five handsheets, mark out six viewing areas. Each viewing area shall be 625 mm². This step can be facilitated by having previously made a transparent plastic overlay grid with these areas cut out.

38.9 With the viewer and the steel rule, count the shives that exceed 1.5 mm in length that are viewed within each of the six areas. Record the total number of shives in each handsheet.

39. Calculation

39.1 Add the total shives found in all five handsheets. This sum multiplied by 53 yields the shive count expressed as shives per square metre.

39.2 The shive count may be calculated for shives per kilogram if the handsheet area is 0.02 m². Shives per kilogram is the product of total shives counted times 888. This multiplier is valid only for the standard handsheets in accordance with TAPPI T 205 with a grammage of 60 ± 1.2 g/m² and an area of 0.02 m².

40. Report

40.1 Report the disintegration time if more than 10 min.

40.2 Report the shive count as shives per square metre or as shives per kilogram as agreed upon between the supplier and the purchaser.

41. Precision and Bias

41.1 *Precision*—From a round-robin test involving 3 laboratories, a coefficient of variation between laboratories in the order of 300 was obtained, at a level of 5000 to 8000 shives/m².

41.2 *Bias*—No statement of bias can be made because of the unavailability of standard reference material.

DIRT IN PULP

42. Significance and Use

42.1 Dirt content is one indication of the quality of the pulp. This measure gives only a visual indication of contamination. The nature of foreign particles is very significant in determining whether the contamination is detrimental to the end-product use. TAPPI T 445 may be appropriate for identification of the particulate contamination. This test is useful for control purposes and the comparison of different pulps.

43. Procedure

43.1 Follow TAPPI T 213.

FIBER LENGTH OF PULP

44. Significance and Use

44.1 The fiber length is a means of comparing pulps. The fiber length distribution may affect the forming characteristics, which in turn influence the physical characteristics of the end-product. This method is useful for control purposes, the comparison of different pulps, and research.

45. Procedure

45.1 Follow TAPPI T 232, T 233.

RESISTANCE OF PULP TO DISINTEGRATION (STANDARD RPG)

NOTE 6—The method described herein is essentially an adaptation of TAPPI UM 252, with several significant changes. The method is complete and no reference to UM 252 is required in its use.

46. Terminology

46.1 *Definitions of Terms Specific to This Standard:*

46.1.1 *resistance to disintegration, n*—the amount of work (expressed as revolutions per gram of pulp) required under standard conditions to bring a sample of pulp to a state of complete dispersion of single fibers.

47. Significance and Use

47.1 Resistance to disintegration is important in that it is a measure of repulpability. The method is useful for control purposes and the comparison of different pulps.

48. Apparatus

48.1 *Disintegrator*—TAPPI standard disintegrator in accordance with T 205; equipped with a 2 L standard vessel, timer/timer controlled power source, 1-s maximum time division.

48.2 *Handsheet Machine*—British Standard sheet machine in accordance with T 205, with couch roll, couch plate, 8 by 8-in. (200 by 200-mm) blotters, and a hot plate.

48.3 *Beakers*—Set of twelve numbered 50-mL beakers and set of twelve numbered 600-mL beakers.

48.4 *Graduated Cylinder, 500-mL*, transparent.

48.5 *Vessel* to contain 1500 mL or more pulp, calibrated at 1500 mL.

48.6 *Sample Cup*, to hold 50 mL of pulp slurry.

48.7 *Oven*, drying, controlled at $105 \pm 3^\circ\text{C}$.

48.8 *Balance*, to weigh up to 100 g with 0.1-g accuracy.

48.9 *Weighing Bottle*, to hold 10 g of pulp.

48.10 *Light Box*—Source of uniform illumination (incandescent or fluorescent) with surface sufficiently large to hold two handsheets—160-mm diameter disks.

49. Test Specimens

49.1 From the sample obtained as specified in Section 6, weigh out three specimens each equivalent to 60 g of moisture-free pulp. Determine the moisture content in accordance with Sections 32-34. Tear, do not cut, the test specimen from the test unit.

50. Procedure

50.1 Connect the disintegrator to the timed power outlet, and fill the disintegrator vessel with 2 L of water ($25 \pm 5^\circ\text{C}$). Select a disintegration period appropriate to the resistance of the pulp to disintegration.

NOTE 7—The times shown below may be used as a guide for selecting the appropriate disintegration period.

Resistance of Pulp to Dispersion	Disintegration Period
slight	15
moderate	30
high	45

50.1.1 Take one specimen and briefly immerse it in the water in the disintegrator vessel to wet it thoroughly (for example, for 15 s) in water at $25 \pm 5^\circ\text{C}$. Tear the specimen into pieces about 20 mm square. If the pulp is flash dried it may be split so that the specimen pieces are about 2.5 mm thick.

50.1.2 Quickly put the torn specimen into the disintegrator vessel and start the disintegration/sampling sequence. Disintegrate the specimen for one period, stop the disintegrator, remove 50 mL of the pulp slurry, and put it into beaker No. 1 (50 mL). The sampling operation should be performed in 1 min or less to minimize any soaking effects that might arise during longer time periods.

NOTE 8—On occasion, lumps of pulp will tend to remain stationary, caught in the flutings on the disintegrator vessel wall. It is necessary to ensure that any such lumps are mixed back into the bulk of the pulp slurry to ensure uniform disintegration response.

50.1.3 Repeat this sequence eleven more times, yielding a total of twelve slurry specimens.

50.2 Make up the first slurry specimen to 1.5 L with tap water ($25 \pm 5^\circ\text{C}$), and pour 500 mL into the transparent cylinder. Cover the cylinder with one hand, and turn end-over-end twice to mix the stock. Inspect the contents of the cylinder by viewing the slurry against a light source. Note the appearance of the slurry relative to these stages of disintegration:

- (a) (a) gross lumps of pulp
- (b) (b) few lumps/many fiber bundles
- (c) (c) few fiber bundles
- (d) (d) no fiber bundles

50.2.1 Make a handsheet from 500 mL of the diluted stock, couch it, and dry it on the hot plate (between the blotters), and mark the handsheet with the slurry specimen number. It is not necessary to press, or air-dry the handsheet, as it will only be used for visual inspection.

50.2.2 Repeat the stock dilution, inspection, and sheet marking for the 11 remaining slurry specimens.

50.2.3 Subject the remaining stock to a further disintegration of 20 min; then sample and prepare a handsheet in accordance with 50.2 and 50.2.1. This further 20-min disintegration will yield stock and handsheet specimens that are considered to be fully disintegrated reference specimens.

50.3 Place the No. 1 sheet (first slurry sample) on the light box, and inspect it. Note the appearance of the sheet as in 50.2. The sheet may be compared with the reference sheet made in accordance with 50.2.3 which is considered to be fully disintegrated.

50.3.1 Compare the remaining 11 sheets, noting at which point complete disintegration is obtained, and at which no change is observed in later specimen handsheets.

50.4 Repeat 50.1.1-50.3.1 except 50.2.3, using disintegration period such that complete disintegration will be achieved in not less than four but not more than ten disintegration periods.

50.4.1 Test two specimen lots to conform to the above requirement.

51. Calculation

51.1 Calculate the resistance to disintegration as follows:

$$\text{Resistance to disintegration expressed in revolutions per gram (RPG)} = n t S / [60 - 0.75 (n - 1)]$$

where:

- n = number of periods to complete disintegration,
- t = disintegration period in minutes, and
- S = speed of disintegrator (usually 3000 rpm)

The $[60 - 0.75 (n - 1)]$ term corrects for the withdrawal of the specimen masses from the slurry.

NOTE 9—As the slurry specimens are withdrawn, the mass of pulp remaining is progressively reduced. The “first” slurry specimen experiences a RPG of:

$$1 t \times 3000/60 \quad (4)$$

The second experiences the same as the first plus:

$$1 t \times 3000/(60 - 1.5) \quad (5)$$

Averaging such a sum for the n th slurry specimen, it will have undergone an RPG of:

$$n t \times 3000/60 - [(1/2) (n - 1) (1.5)] \text{ or } n t \times 3000/60 - 0.75 (n - 1) \quad (6)$$

52. Report

52.1 Report the mean of two resistance to disintegration determinations, giving the mean, and range to two significant figures.

52.1.1 Report if the disintegrator was run at any speed other than 3000 rpm.

53. Precision and Bias

53.1 The precision of this test has not been determined. No statement can be made about the bias of this test since a standard material is not available.

LABORATORY PROCESSING OF PULP (BEATER METHOD)

54. Significance and Use

54.1 The beater method is used to evaluate the relative refining behavior of pulp. The refining behavior is characterized by the change with time of freeness (or slowness), and the development of physical sheet properties (see sections below). This test is useful for control tests, the comparison of different pulps, and research.

55. Procedure

55.1 Follow TAPPI T 200.

FREENESS (CANADIAN STANDARD FREENESS)

56. Significance and Use

56.1 Freeness (or slowness) is a measure of the drainage rate of a pulp slurry. Drainage rate is commonly used to indicate the degree of refining of a pulp.

NOTE 10—Other drainage rate measures used in the paper industry include:

(a) (a) Schopper Riegler Freeness (Slowness) SCAN MS:65 Drainability of Pulp by Schopper Riegler Method.

(b) (b) Drainage Time of Pulp. TAPPI Standard Method T 221.

(c) (c) Drainage Time for Insulating Board. TAPPI Standard Method T 1002.

(d) (d) Freeness of Pulp (Williams Tester). TAPPI Useful Method UM 203.

57. Procedure

57.1 Follow TAPPI T 227.

FORMING HANDSHEETS FOR PHYSICAL TESTS OF PULP

58. Significance and Use

58.1 The forming of handsheets permits the comparison of pulps with respect to their physical properties at different degrees of refining.

59. Procedure

59.1 Follow TAPPI T 205.

AIR RESISTANCE (POROSITY)

60. Significance and Use

60.1 Air resistance measurements on handsheets allow the comparison of pulps with respect to the development of air resistance with degree of refining. Air resistance is related to the dielectric strength and absorbency of electrical insulations.

61. Procedure

61.1 Make pulp handsheets for testing in accordance with Section 59.

61.2 Test for air resistance in accordance with Test Methods D 202.

BURSTING STRENGTH**62. Significance and Use**

62.1 Bursting strength has considerable use as a control test to indicate general physical strength. This method is useful for comparing the potential bursting strength of different pulps at specified degrees of refining.

63. Procedure

63.1 Make pulp handsheets in accordance with Section 59.

63.2 Test for bursting strength in accordance with Test Methods D 202 and D 774.

FOLDING ENDURANCE (M.I.T.)**64. Significance and Use**

64.1 Folding endurance of paper is a measure of its toughness and brittleness. It is sensitive to changes in the paper, and may be used as a measure of thermal aging. This method is useful for comparing the potential folding strength of different pulps at specified degrees of refining.

65. Procedure

65.1 Make pulp handsheets in accordance with Section 59.

65.2 Test for folding endurance in accordance with Test Methods D 202 and D 2176.

APPARENT DENSITY**66. Significance and Use**

66.1 Many physical and electrical properties of paper are related to the apparent density. The ease with which a sheet of desired density can be obtained is an important measure of the usefulness of a pulp. This method is useful for comparing the potential density of insulations made from different pulps of specified degrees of refining.

67. Procedure

67.1 Make pulp handsheets in accordance with Section 59.

67.2 Determine density in accordance with Test Methods D 202, Method B.

TENSILE PROPERTIES**68. Scope**

68.1 This test method includes procedures for determination of tensile strength, elongation, and tensile energy absorption (TEA) on pulp handsheets. Any or all of the three properties may be determined, as may be desired.

69. Significance and Use

69.1 This test is useful in determining the potential tensile properties of products which will be made from the pulp being studied; and the effects of refining operations on the potential tensile properties.

69.2 See the applicable sections of Test Methods D 202 for further information on significance of the individual properties.

70. Procedure

70.1 Prepare pulp handsheets in accordance with Section 59.

70.2 Determine the specified tensile properties of the handsheets in accordance with the method for Tensile Properties as given in Test Methods D 202, except use an initial test span of 51 ± 3 mm (2.0 ± 0.1 in.) and a speed of 6 mm/min (0.25 in./min) when determining TEA.

71. Report

71.1 Report in accordance with Section 7 and the applicable sections of Test Methods D 202.

72. Precision and Bias

72.1 Refer to the applicable sections of Test Methods D 202.

ANALYSIS OF ASH FOR CATIONS BY ATOMIC ABSORPTION SPECTROMETRY**73. Significance and Use**

73.1 The ash of pulp for electrical insulation may contain cations such as sodium, potassium, calcium, and magnesium. The presence of these cations may affect the dielectric characteristics and service performance of electrical paper made from the pulp. Cations may react with process constituents in the paper-making process, forming undesirable precipitates.

73.2 This test determines sodium, potassium, calcium, and magnesium from one dissolved ash specimen.

74. Interferences

74.1 The analysis of calcium, magnesium, potassium, and sodium in unbleached wood pulp should not be subject to interferences, and may be analyzed without the addition of an interference suppressant.

75. Apparatus and Materials

75.1 Use apparatus and chemicals as specified in Test Method D 2576.

76. Reagents

76.1 *Water*— Use reagent water conforming to the requirements in Specification D 1193, for Reagent Water Type I, whenever water is specified in this method.

76.2 *Hydrochloric Acid* (sp gr 1.19)—Concentrated hydrochloric acid (HCl).

76.3 *Hydrochloric Acid* (1 + 99)—Add 1 volume of HCl (sp gr 1.19) to 99 volumes of water.

76.4 *Stock Solutions*—Purchased solutions will have the expiration date on the label. Solutions prepared in the testing laboratory should be stable for 1 year, if kept in well-stoppered polyethylene bottles.

76.4.1 *Calcium* (1 mL = 1.0 mg Ca, equivalent to 1000 mg/L Ca)—Weigh 2.497 g of calcium carbonate (CaCO_3) and transfer it to a 500-mL Erlenmeyer flask. Add 10 mL of water. Pour 10 mL of HCl (sp gr 1.19) slowly down the side of the

flask. Add an additional 200 mL of water, and heat until solution is complete. Cool and dilute to 1 L.

76.4.2 *Magnesium* (1 mL = 0.1 mg Mg, equivalent to 100 mg/L Mg)—Dissolve 1.0135 g of magnesium sulfate heptahydrate (MgSO₄·7H₂O) in 200 mL of water, and dilute to 1 L.

76.4.3 *Potassium* (1 mL = 1 mg K, equivalent to 1000 mg/L K)—Dissolve 1.907 g of potassium chloride (KCl) in 1 L of water.

76.4.4 *Sodium* (1 mL = 1 mg Na, equivalent to 1000 mg/L Na)—Dissolve 2.542 g of sodium chloride (NaCl) in 1 L of water.

76.5 *Standard Solutions*—Dilute the stock solutions with HCl (1 + 99) to prepare the standards to be used for calibration. These solutions should be made immediately before use, since they have limited stability.

77. Calibration

77.1 Prepare at least three standard solutions containing known concentrations of each of the metal ions to be determined, by diluting the stock solutions as described in 76.5. Prepare the standards so that they bracket the expected values for the diluted unknown. The standards and the diluted unknown must be made up to fall within the linear concentration range of the element.

77.2 Atomize the standards through the instrument, following the instruction manual for the instrument, and using the following wavelength settings:

Metal	Wavelength, nm
Calcium	422.7
Magnesium	285.2
Potassium	766.5
Sodium	589.0 or 589.6

77.3 If the instrument is equipped with a direct concentration readout, adjust the readout to give the concentration of the standards.

77.4 If the instrument does not have a direct concentration readout, prepare a calibration curve by plotting on linear graph paper the absorbance against standard concentration for each standard.

78. Procedure

78.1 Ash the pulp specimen as specified in Sections 82-85.

78.2 Add 5 mL of HCl (1 + 1) [add 1 volume of HCl sp gr 1.19 to 1 volume of water] to the ash. Swirl the mixture to dissolve the ash.

78.3 Wash a slow, very retentive ashless filter paper¹¹ with HCl (1 + 1).

78.4 Filter the ash solution through the ashless filter paper directly into a 100-mL volumetric flask. Wash the filter paper with several small aliquots of HCl (1 + 1). Dilute to volume with water.

78.5 Prepare a blank solution in accordance with 78.1-78.4, omitting the ash specimen.

78.6 Determine the concentrations of calcium, magnesium, potassium, and sodium in each solution by atomizing the solutions through the atomic absorption spectrophotometer.

This should be done immediately after the instrument is calibrated with the standards. The linear concentration ranges are as follows:

Metal	Linear Concentration Range, mg/L
Calcium	0.3 to 15.0
Magnesium	0.05 to 3.5
Potassium	0.04 to 4.0
Sodium	0.02 to 2.0

78.7 The measuring range can be increased by dilution of the specimen solution. In unbleached sulfate wood pulps, it is often found that dilution is unnecessary for analysis of potassium, but that for analysis of calcium, magnesium or sodium, a dilution of 1 + 19 with water is required before analysis. The lower limits of measurement are largely dependent on the equipment, as described in Method D 2576.

79. Calculation

79.1 Calculate the cation contents of the pulp specimen as follows:

$$\text{Cation content, } \mu\text{g/g} = (A - B) \times D \times 100/C \quad (7)$$

where:

A = cation in unknown solution, mg/L,

B = cation in blank solution, mg/L,

C = weight of moisture-free pulp specimen, g, and

D = dilution factor.

80. Report

80.1 Report in accordance with Section 7, and include the results in micrograms per gram of moisture-free pulp for the cations that were determined.

81. Precision and Bias

81.1 The cation content of intralaboratory duplicate samples should agree within 10 %.

81.2 Interlaboratory results may show differences of up to 30 % for magnesium, and up to 300 % for potassium, sodium, and calcium.

81.3 Bias is unknown.

ASH CONTENT

82. Significance and Use

82.1 The ash content of pulp depends upon the type of fiber, treatment at the pulp mill, and the washing of the pulp. It is a general indicator of quality.

82.2 The ash content may affect the electrical properties and the heat stability of the paper made from the pulp. This test is useful for routine acceptance testing, comparison of different pulps, and research.

83. Procedure

83.1 Determine the ash content as specified in Test Methods D 202, and Method A (TAPPI T 413).

84. Report

84.1 Report in accordance with Section 7 and Test Methods D 202 (TAPPI T 413).

¹¹ Whatman filter paper, No. 42, has been found satisfactory for this test method.

85. Precision and Bias

85.1 The results of duplicate ash determinations should be suspect if they differ by more than the following:

Weight of Ash, mg	Maximum Acceptable Difference, mg
Over 50	3
Over 20 to 50	2
Up to 20	1

85.2 Precision between laboratories is 0.13 % ash content.

85.3 Precision estimates are based on a round-robin test among five laboratories.

85.4 Bias is unknown.

86. Keywords

86.1 air resistance ash analysis; ash content; apparent density; bulk characteristics; bursting strength; cellulose; cellulosic fiber; conductivity; dirt; disintegration; extractable acidity-alkalinity; extractable chlorides; fiber analysis; fiber length of pulp; folding endurance; freeness (Canadian Standard Freeness); handsheet characteristics; handsheet machine; Kappa/Permanganate number; moisture; pentosan content; pH; pulps; shive count; solvent soluble matter; tensile strength; water

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).