



Standard Practice for Effect of Water on Bituminous-Coated Aggregate Using Boiling Water¹

This standard is issued under the fixed designation D 3625; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a rapid procedure for visually observing the loss of adhesion in uncompacted bituminous-coated aggregate mixtures due to the action of boiling water.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 1 Specification for ASTM Thermometers²

D 979 Practice for Sampling Bituminous Paving Mixtures³

3. Summary of Practice

3.1 A bituminous-coated aggregate mixture sample is placed in a container of boiling distilled water and boiled for 10 min. After cooling the boiled mixture, visual observation is made of retained bitumen coating on the aggregate.

4. Significance and Use

4.1 This practice is useful as an indicator of the relative susceptibility of bituminous-coated aggregate to water, but should not be used as a measure of field performance because such correlation has not been established. If loss of adhesion due to water is indicated, testing by other procedures should be conducted to further evaluate the mixture.

4.2 This practice should not be used for acceptance/rejection by owner agencies.

5. Apparatus

5.1 *Scoop*, shovel or other implement capable of removing a representative sample from a larger mass of bituminous-coated aggregate mixture.

5.2 *Glass Beakers*, heat-resistant, 1000–2000 mL capacity or suitable metal containers of similar dimensions and capacity.

¹ This practice is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.22 on Effect of Water and Other Elements on Bituminous-Coated Aggregates.

Current edition approved Sept. 10, 1996. Published November 1996. Originally published as D 3625 – 77. Last previous edition D 3625 – 91.

² *Annual Book of ASTM Standards*, Vol 14.03.

³ *Annual Book of ASTM Standards*, Vol 04.03.

5.3 *Source of Distilled Water* (at least 500 mL (½ qt) for each test) (Note 1).

NOTE 1—Water that is not distilled has been shown to significantly affect results of the procedure and should not be used.

5.4 *Device for Heating Water*—gas burner with wire gauze supported on tripod or ring, hot plate, camp stove or other suitable device which will distribute heat evenly.

5.5 *Thermometers*—ASTM low-distillation thermometers graduated either in Celsius or Fahrenheit as specified, having a range from –2 to +300°C or 30 to 580°F respectively, and conforming to the requirements for thermometer 7C or 7F as prescribed in Specification E 1.

6. Sample Preparation

6.1 Prepare an uncompacted bituminous-coated aggregate mixture following established laboratory procedures or obtain a sample of plant-produced mixture in accordance with Practice D 979. The temperature of hot mixtures shall be below the boiling temperature of water, but not less than 85°C (180°F), before placing in boiling water. The temperature of mixtures that are cold mixed shall be at or above room temperature before placing in boiling water.

7. Procedure

7.1 For each sample tested pour distilled water into a clean container (as described in 5.2) such that the container is approximately half full and heat to boiling.

7.2 With an appropriate implement (as described in 5.1) place approximately 250 g (½ lb) of the bituminous-coated aggregate mixture in the boiling water while the container is exposed to the heat source. Bring the water back to boiling and maintain boiling for 10 min ± 15 s. Avoid excessive manipulation of the bituminous-coated aggregate mixture.

7.3 At the end of 10 min, remove the container from the heat source. Skim off any free bitumen from the surface of the water to prevent recoating. Cool to room temperature, decant the water, and empty the wet mix onto a white paper towel.

NOTE 2—For comparison, a similar amount of fresh bituminous-coated aggregate mixture should be placed into a second container, covered with unheated distilled water for 10 min, the water decanted and the mixture emptied onto a white paper towel.

7.4 Visually observe the aggregate (coarse and fine) for retained bitumen coating. Any thin, brownish, translucent areas

are to be considered fully coated. Visual observations shall be made immediately after the sample is placed on the white paper towel (Note 3). Examination of the sample under a light and with low magnification may aid in the visual observation of retained coating.

NOTE 3—Additional information can be obtained by repeating the visual observation 24 h after boiling when the sample has dried and the

effects of moisture on the coating appearance of the sample have been eliminated.

8. Keywords

8.1 bituminous paving mixtures; coating/stripping; loss of adhesion; water

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).